

IMPRESSIONS BAYSIDE




Sand



Dust



Reed



Dune



Stone



Mist

IMPRESSIONS BAYSIDE

SPECIFICATION	BAYSIDE	BAYSIDE PLUS
FIBER CONTENT	100% Solution Dyed Polyester	100% Solution Dyed Polyester
FACE WEIGHT OZ/YD ²	16	25
FINISHED PILE THICKNESS	12/32 (0.375 inch)	16/32 (0.50 inch)
TUFTS PER INCH	6.5	8
PILE DENSITY	1536	1800
YARN TWIST	4.50 tpi	4.50 tpi
GUAGE	5/32 CP	5/32 CP
PRIMARY BACKING	Polypropylene	Polypropylene
SECONDARY BACKING	FlexBack	FlexBack
TOTAL WEIGHT OZ/YD ²	42	53
WIDTH	12'	12'
DYE METHOD	Solution Dyed	Solution Dyed
TREATMENT	Soil & Stain	Soil & Stain
FLAMMABILITY	Pill Test (CPSC FF1-70) Passed	Pill Test (CPSC FF1-70) Passed